

TECHNICAL DATA SHEET

P. 8

AQUAVINTAGE 2C

PRODUCT DESCRIPTION:

Water based reactive stain, specially fit for ageing the wood in a simple and fast way. Can also react on wood that is not containing tannin.

RANGE OF APPLICATION:

Industrial application for Wood Flooring and wood panels. Only for interior use

APPLICATION

preparation substrate	Prepare the wood according the rules of the art and remove the sanding dust carefully
processing:	Mix the Aquavintage 2C with the Activator 1/1. During the application of the stain, stirr regularly. • Stirr well before use. • Spraying : apply +/- 50g/m ² , even outing with a brush. • Manual application : apply theAquavintage 2C ca 50g/m ² with a brush in the direction of the wood fiber. even outing afterwards with a brush.

PROTECTION

After respecting the reaction time, it is recommended to aplly 1 coat of Ecofix or Oculto to block the color before protecting with an oil or a lacquer.

IMPORTANT INFORMATION

· Respect reaction time.

• The final color depends on the type of wood, sanding, wood preparation and the applied quantity. For this reason its always recommended to make a test first before starting production.

- Only use stainless material.

- Clean all material immediately after use.

APPLICATION MATERIAL



PACKING 5lt



SHELF-LIFE

In well-closed and original packing: minimum 12 months

WAREHOUSING

by 10 - 40 °C

CLEANING

HYDRO CLEANER 7984

ATTENTION A "All tests and application methods are done with the above-mentioned Debal Coatings components. We are not responsible for application with other materials, unless written agreement from Debal Coatings"

PRODUCED BY DEBAL COATINGS NV Industrieweg 29 - 8800 Beveren-Roeselare - Belgium Tel. +32 (0)51 30 11 40 - Fax. +32 (0)51 31 26 48 ciranova@ciranova.be

TECHNICAL DATA

extra component:	ACTIVATOR AQUAVINTAGE 2C
mixing ratio:	50:50
pot-life:	ca 3 weeks
density:	+/- 1.00 KG/L
viscositv:	as water

viscosity:	as water
colors:	8 COLORS AVAILABLE
solid content:	-
gloss:	-
thinner:	-
coverage per coat:	ca 50g/m ²
Coverage USA per coat: ca 5 g/ft ²	
drying:	Reaction time: minimum 12 hrs